

Lumirror. F65

Applications

- · Hot stamping
- Casting
- · Release Liner

— Mono layer PET

PLAIN PET FILM

Summary

F65 is designed for easy handling during processing, especially in hot stamping applications. This film is also designed to avoid the formation of heat wrinkles in the machine direction during drying operations.

Lumirror F65



✓ Technical Data *											
PROPERTIES		METHOD	UNITS								<u>ရ</u>
Thickness		-	0.00001"	46	48	60	75	92	142	200	ıct
Nominal Yield		-	in²/lb	43,000	41,200	32,900	26,400	21,500	13,900	9,900	\Box
F-5 •	MD	ASTM D882	lb/in² •	15,100	15,100	15,200	15,400	14,900	14,600	14,800	ata
	TD			13,900	13,900	13,700	13,700	14,100	13,700	13,900	
Tensile Strength at Break	MD	- ASTM D882	lb/in² •	35,300	35,400	34,600	35,300	30,300	24,700	24,500	he
	TD			34,400	34,300	32,700	32,700	34,400	27,000	28,700	et
Elongation at Break	MD	– ASTM D882	% •	130	130	130	130	160	170	180	_
	TD			120	120	130	140	130	130	140	_
Heat Shrinkage (150°C for 30 minutes)	MD	– ASTM D1204	. % -	1.6	1.6	1.5	1.5	1.4	1.1	1.2	_
	TD			0.3	0.3	0.1	0.2	0.2	0.2	0.1	_
Heat Shrinkage (190°C for 20 minutes)	MD	– ASTM D1204	% -	3.6	3.5	3.1	3.0	2.7	2.0	2.0	_
	TD			0.7	0.7	0.3	0.3	0.8	0.5	0.3	_
Coefficient of Friction	A-side vs. B-side	ASTM D1894	μ_{S}	0.4	0.4	0.4	0.4	0.4	0.4	0.4	_
			μ_{D}	0.3	0.3	0.3	0.3	0.3	0.3	0.3	_
Haze (1 sheet)		ASTM 1003	%	3.0	3.0	3.5	3.5	3.5	4.0	7.0	_


Key Features

- High strength and good handling properties
- · Low coefficient of friction which facilitates smooth coating and finishing
- Resistant to heat wrinkle formation in the machine direction during coating process

Similar Products

- F6L
- F7S
- F7R

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Lumirror * is a registered trademark of Toray Industries, Inc. for its range of Polyester Films based on Polyethylene Terephthlate (PET).