


# LUMIRROR<sup>®</sup> F65B

## Applications

- Brushing



Lumirror F65B

## PLAIN PET FILM

## Summary

F65B is designed for easy handling during processing, especially in brushing applications. This type is also designed to avoid the formation of heat wrinkles in the machine direction during drying operations.

## Technical Data \*

PROPERTIES		METHOD	UNITS	TYPICAL VALUES
Thickness		-	micron	50.8
Nominal Yield		-	m <sup>2</sup> /kg	14.1
F-5	MD	ASTM D882	Mpa	102
	TD			96
Tensile Strength at Break	MD	ASTM D882	Mpa	169
	TD			198
Elongation at Break	MD	ASTM D882	%	180
	TD			140
Heat Shrinkage (150°C for 30 minutes)	MD	ASTM D1204	%	1.2
	TD			0.1
Heat Shrinkage (190°C for 20 minutes)	MD	ASTM D1204	%	2.0
	TD			0.3
Coefficient of Friction	A-side vs. B-side	ASTM D1894	μ <sub>s</sub>	0.4
			μ <sub>b</sub>	0.3
Haze (1 sheet)		ASTM 1003	%	7.0


## Key Features

- High strength and good handling properties
- Low coefficient of friction which facilitates smooth coating and finishing
- Resistant to heat wrinkle formation in the machine direction during coating process

## Similar Products

- F65
- F6L
- F7R

## Winding Direction



## \* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Lumirror® is a registered trademark of Toray Industries, Inc. for its range of Polyester Films based on Polyethylene Terephthalate (PET).