
LUMIRROR® FA5

Applications

- Graphics
- Label



TWO LAYER PET FILM, ONE SIDE LOW GLOSS

Summary

FA5 is a low gloss film with moderate to low haze compared to other matte films. The low gloss side is directly printable with no secondary treatment required.

umirror FA



✓ Technical Data **

PROPERTIES Thickness		METHOD -	UNITS 0.00001"	TYPICAL VALUES 92
F-5	MD	- ASTM D882	lb/in² ——	14,800
	TD			16,400
Tensile Strength at Break	MD	- ASTM D882	lb/in² ——	33,600
	TD			40,400
Elongation at Break	MD	- ASTM D882	%	160
	TD			120
Heat Shrinkage (150°C for 30 minutes)	MD	• ASTM D1204	%	2.2
	TD			2.8
Coefficient of Friction	A-side vs. B-side ASTM	ASTM D1894	μ _s	0.4
		A31WLD1694	μ_{D}	0.3

Key Features

- · Low gloss side with low contact haze
- The PET side has the standard properties of a plain polyester film
- Excellent handling
- Complies with US FDA 21 CFR 177.1630 requirements for food packaging applications

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.