


Lumirror.MK6HB

Applications

- Confections
- Snacks
- Coffee
- Pet food
- Foil replacement



Lumirror MK6HB

BEST METALLIZED
BARRIER PET FILM
IN THE INDUSTRY

Summary

MK6HB is an ultra high oxygen and moisture barrier metallized PET film.

Please note :

- The metallized side is not suitable for water based inks or adhesives.
- The amorphous PET adhesion layer is suitable for both water and solvent based inks or adhesives.

Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES		
Thickness		-	0.00001"	36	48	92
Nominal Yield		-	in ² /lb	55,700	41,200	21,500
F-5	MD	ASTM D882	lb/in ²	14,600	15,200	15,400
	TD			14,500	15,100	15,100
Tensile Strength at Break	MD	ASTM D882	lb/in ²	35,300	36,700	36,800
	TD			36,400	37,500	36,800
Young's Modulus	MD	ASTM D882	lb/in ²	662,800	708,300	724,000
	TD			753,800	799,300	725,400
Elongation at Break	MD	ASTM D882	%	110	120	140
	TD			100	110	140
Heat Shrinkage (150°C for 30 minutes)	MD	ASTM D1204	%	2.6	2.6	2.6
	TD			2.2	1.9	2.1
Coefficient of Friction	A-side vs. B-side	ASTM D1894	μ _s	0.5	0.6	0.7
			μ _b	0.5	0.6	0.6
Optical Density		ASTM 1003		2.8	2.8	2.8
MVTR - 100 °F, 50% RH		ASTM F1249	g/100in ² /day	0.005	0.005	0.005
O ₂ Barrier - 73 °F, 0% RH		ASTM D3985	cc/100in ² /day	0.005	0.005	0.005


Key Features

- Ultra-high barrier to oxygen, moisture and other gases
- Excellent aroma and organoleptic barrier
- Good machinability due to surface roughness properties
- Excellent dimensional stability at higher temperatures
- Improved adhesion of inks, adhesives and polyethylene on the amorphous PET adhesion layer
- Complies with US FDA 21 CFR 177.1630 requirements for food packaging applications

Winding Direction

Adhesion Surface

Metal Side



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Lumirror® is a registered trademark of Toray Industries, Inc. for its range of Polyester Films based on Polyethylene Terephthalate (PET).