


Lumirror TA30

# LUMIRROR® TA30

### **Applications**

- Graphic and optical
- Over-laminate for labels
- Decorative



## SUPER CLEAR THREE LAYER PET FILM

## Summary

TA30 is a low haze multilayer PET film type intended for over-laminate for label applications and for graphic and optical application.

www.toraytpa.com rimarketing@toraytpa.com Toray Plastics (America), Inc. 50 Belver Avenue North Kingstown, RI 02852 1.800.453.6866



#### Lumirror TA30

#### Technical Data \*

PROPERTIES Thickness		METHOD	UNITS	TYPICAL VALUES			
			micron	12.2	23.4	36.1	50.8
Nominal Yield		-	m2/kg	58.5	30.5	19.8	14.1
F-5	MD	ASTM D882	Мра 🗕	109	102	111	106
	TD			100	95	107	101
Tensile Strength at Break	MD	ASTM D882	Мра 🗕	272	206	228	185
	TD			253	226	248	214
Elongation at Break	MD	ASTM D882	% -	120	170	140	180
	TD			130	150	110	130
Heat Shrinkage (150°C for 30 minutes)	MD	ASTM D1204	% -	1.6	1.2	1.7	1
	TD			0.8	0.4	0.6	0.7
Heat Shrinkage (190°C for 5 minutes)	MD	ASTM D1204	% -	3.1	2.1	3.6	1.9
	TD			1.5	0.6	2.0	1.1
Coefficient of Friction	A-side vs. B-side	ASTM D1894	$\mu_{s}$	0.4	0.4	0.4	0.4
	A-SIGE VS. D-SIGE		μ	0.3	0.3	0.3	0.3
Haze (1 sheet)		ASTM 1003	%	1.1	1.3	1.4	1.4


#### Key Features

• Low haze and good handling accomplished by co-extrusion technology.

#### Similar Products

- U65
- F7S
- TA31
- TA3L

#### Winding Direction



#### ★ These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.