



SUPER CLEAR THREE LAYER PET FILM, ONE SIDE ANTI-STATIC COATING

Summary

TA3A is a multilayer PET film with a super anti-static coating on one side. It has low haze, handles well, and displays excellent release properties.

www.toraytpa.com rimarketing@toraytpa.com Toray Plastics (America), Inc. 50 Belver Avenue North Kingstown, RI 02852 1.800.453.6866



🖉 Technical Data 🗶


Lumirror	ТАЗА 🖊
- VALUES	Product
3.1	ਹਿ
3.7	Data
07	Ita
9	. Sh
97	lee

PROPERTIES		METHOD	UNITS	TYPICAL VALUES
Thickness		-	micron	38.1
Nominal Yield		-	m2/kg	18.7
F-5	MD	ASTM D882	Мра —	107
	TD			99
Tensile Strength at Break	MD	ASTM D882	Мра 🗕	197
	TD			225
Elongation at Break	MD	ASTM D882	% —	170
	TD			130
Heat Shrinkage (150°C for 30 minutes)	MD	ASTM D1204	%	1.3
	TD			0.2
Heat Shrinkage (190°C for 5 minutes)	MD	ASTM D1204	% -	2.3
	TD			0.6
Coefficient of Friction	A-side vs. B-side	ASTM D1894	μ _s	0.3
	A-side vs. B-side		μ _D	0.2
Haze (1 sheet)		ASTM 1003	%	1.5
Surface Resistivity		ASTM D257	ohm/sq	E5

Key Features

- Super anti-static properties accomplished by coating technology
- Controls oligomer to prevent bleed-out to the surface
- Low haze and good handling accomplished by co-extrusion technology
- Compared with current anti-static PET, this film has very low surface resistivity (E5) and excellent release properties even at low humidity

Winding Direction



★ These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose. Lumirror TA3A