


LUMIRROR® TA3L

Applications

- Thermal lamination



Lumirror TA3L

SUPER CLEAR THREE
LAYER PET FILM WITH
BALANCED SHRINKAGE

Summary

TA3L is a low haze multi-layer PET film with balanced shrinkage properties. TA3L is designed specifically for thermal lamination applications.

Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES
Thickness		-	micron	50.8
Nominal Yield		-	m ² /kg	14.1
F-5	MD	ASTM D882	Mpa	109
	TD			115
Tensile Strength at Break	MD	ASTM D882	Mpa	208
	TD			256
Elongation at Break	MD	ASTM D882	%	160
	TD			110
Heat Shrinkage (150°C for 30 minutes)	MD	ASTM D1204	%	1.5
	TD			1.9
Coefficient of Friction	A-side vs. B-side	ASTM D1894	μ_s	0.4
			μ_b	0.3
Haze (1 sheet)		ASTM 1003	%	1.4


Key Features

- Balanced heat shrinkage
- Low haze with excellent handling properties

Similar Products

- F6L
- TA30

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Lumirror® is a registered trademark of Toray Industries, Inc. for its range of Polyester Films based on Polyethylene Terephthalate (PET).