


## TORAYFAN F62W

## **Applications**

- Confections
- Snacks
- Bakery
- · Pet food
- Ag/Chem
- Medical



oravfan F62\

# ONE SIDE TREATED, ONE SIDE HEAT SEALABLE BOPP PRINT WEB

### Summary

One side treated with Toray's Ultra High Surface Energy (UHSE) and one side heat sealable Bi-Axially Oriented Polypropylene film. The heat seal layer contains slip additives for low and consistent COF. Designed to be the outside print web for VFFS applications.



#### Technical Data \*

PROPERTIES		METHOD	UNITS	TYPICAL VALUES			
Thickness		-	micron	15	18	23	25
Nominal Yield		-	m²/kg	73	63	48	44
Tensile Strength at Break -	MD	— ASTM D882	MPa	100	100	100	100
	TD			300	300	300	300
Young's Modulus -	MD	— ASTM D882	MPa	2,200	2,200	2,200	2,200
	TD			3,800	3,800	3,800	3,800
Elongation at Break -	MD	— ASTM D882	%	200	200	200	200
	TD			60	60	60	60
Heat Shrinkage (140°C for 15 minutes)	MD	— ASTM D1204	%	8	8	8	8
	TD			5	5	5	5
Coefficient of Friction (Sealant Side)		ASTM D1894 -	$\mu_{\scriptscriptstyle s}$	0.33	0.33	0.33	0.33
			$\mu_{\text{d}}$	0.28	0.28	0.28	0.28
Gloss (60°)		ASTM D2457	GU	130	130	130	130
Haze (1 sheet)		ASTM 1003	%	2.6	2.6	2.6	2.6
Wetting Tension		ASTM D2578	dyne/cm	41	41	41	41
Heat Seal Strength @ 121°C		1	g/25mm	330	330	330	330
Seal Initiation Temp (>200g/25mm)		1	°C	99	99	99	99
MVTR - 38°C, 90% RH		ASTM F1249	g/m²/day	8.2	7.0	5.3	4.8

<sup>1</sup> Sentinel Sealer model 12 ASL, 0.5 sec, 20 psi. UPPER: flat, Teflon coated. LOWER: rubber with glass cloth, unheated

#### Key Features

- · Excellent print quality and ink adhesion
- · Wide heat seal range for lap seals
- · Excellent bond in adhesive and extrusion laminations
- · Stable slip system for low, continuous COF


#### Similar Products

- F61W
- F71W

#### Typical Structures

- F62W/ink/PE or ADH/F62W lap or fin seal
- F62W/ink/PE or ADH/F71W lap or fin seal
- F62W/ink/PE or ADH/PWX4 lap or fin seal
- F62W/ink/PE or ADH/CBS lap or fin seal
- O.L./ink/F62W fin seal

#### Winding Direction



#### \* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.