


TORAYFAN F63W

Applications

- Confections
- Snacks
- Bakery
- Pet Food
- Ag/Chem
- Medical



ONE SIDE TREATED, ONE SIDE HEAT SEALABLE BOPP PRINT WEB

Summary

One side treated with Toray's Ultra High Surface Energy (UHSE) and one side heat sealable Bi-Axially Oriented Polypropylene film. The heat seal layer contains slip additives for low and consistent COF. Designed to be the outside print web for VFFS applications. Especially designed for high ink bond applications

www.toraytpa.com rimarketing@toraytpa.com Toray Plastics (America), Inc. 50 Belver Avenue North Kingstown, RI 02852 1.800.453.6866



Product Data Sheet

🖉 Technical Data 🗡

Torayfan F63W

| Ξ. | |
|----|--------------|
| | |
| | |
| | — |
| | <u> </u> |
| | Q |
| | Q |
| | 2 |
| | _ |
| | \mathbf{O} |
| | Η. |
| | _ |
| | U |
| | õ |
| | <u> </u> |
| | ā, |
| | |
| | $(\cap$ |
| | <u> </u> |
| | 5 |
| | Μ |
| | 5 |
| | (D) |
| | – |

| PROPERTIES | | METHOD | UNITS | TYPICAL VALUES | |
|--|----|--------------|----------------|-----------------------|-------|
| Thickness | | - | micron | 15 | 18 |
| Nominal Yield | | - | m²/kg | 73 | 63 |
| Tancila Strongth at Broak | MD | – ASTM D882 | MPa | 100 | 100 |
| Tensile Strength at Break | TD | | | 300 | 300 |
| Young's Modulus | MD | – ASTM D882 | MPa | 2,200 | 2,200 |
| Tourig's modulus | TD | | | 3,800 | 3,800 |
| Elongation at Break | MD | – ASTM D882 | % | 200 | 200 |
| | TD | | | 60 | 60 |
| Heat Shrinkage (140°C for 15 minutes) | MD | – ASTM D1204 | % | 8 | 8 |
| | TD | | | 5 | 5 |
| Coefficient of Friction (Sealant Side) | | ASTM D1894 | μ _s | 0.33 | 0.33 |
| | | | μ_{d} | 0.28 | 0.28 |
| Gloss (60°) | | ASTM D2457 | GU | 130 | 130 |
| Haze (1 sheet) | | ASTM 1003 | % | 3 | 3 |
| Wetting Tension | | ASTM D2578 | dyne/cm | 38 | 38 |
| Heat Seal Strength @ 121°C | | 1 | g/25mm | 330 | 330 |
| Seal Initiation Temp (>200g/25mm) | | 1 | °C | 99 | 99 |
| MVTR - 38°C, 90% RH | | ASTM F1249 | g/m²/day | 8.22 | 6.98 |

1 Sentinel Sealer model 12 ASL, 0.5 sec, 20 psi. UPPER: flat, Teflon coated. LOWER: rubber with glass cloth, unheated

Key Features

- Excellent print quality and ink adhesion
- Wide heat seal range for lap seals
- Excellent bond in adhesive and extrusion laminations
- Stable slip system for low, continuous COF


Similar Products

- F61W
- F71W

Typical Structures

- F63W/ink/PE or ADH/F63W lap or fin seal
- F63W/ink/PE or ADH/F71W lap or fin seal
- F63W/ink/PE or ADH/PWX4 lap or fin seal
- F63W/ink/PE or ADH/CBS lap or fin seal
- O.L./ink/F63W fin seal

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Torayfan ® is a registered trademark of Toray Industries, Inc. for its range of bi-oriented Polypropylene Films (BOPP)