
TORAYFAN TF-LT03

Applications

- · Linear Tear
- Flexible Packaging



orayfan TF-LT(

LINEAR TEAR CAST POLYPROPYLENE FILM

Summary

Torayfan TF-LT03 is specifically designed as a inner web in multilayer packing laminations. This film provides a linear tear in the machine direction for easy opening, eliminating the need for laser scoring or microperforation. It can be used in either HFFS or pouch machines in pillow pouch or gusseted applications.

Toray Plastics (America), Inc.
50 Belver Avenue
North Kingstown, RI 02852
1.800.453.6866

✓ Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES
Thickness Range		-	0.00001"	140-500
Thickness	·	-	0.00001"	140
Nominal Yield		-	in²/lb	21,857
Tensile Strength at Break —	MD	– ASTM D882	lb/in²	35,000
	TD			4,500
Elongation at Break —	MD	– ASTM D882	%	30
	TD			400
Heat Shrinkage (212°F for 10 minutes)	MD	ASTM D2732-96	%	3
Coefficient of Friction –	A side	— ASTM D1894	m _D	0.40
	B side		m _D	0.35
Haze (1 sheet)		ASTM 1003	%	30
Surface Tension	Corona			38
Heat Seal Strength @250F		Toray Method	lb/in	15+
Opacity				50


Key Features

- Exceptional linear tear property
- · Available in either clear or white
- · For use with hot-melt, water, UV and solvents
- TD tear resistance

Typical Structures

- F62W/ink/LT03/PWX4
- CBC/ink/LT03/CBS

✓ Winding Direction (2 side treat)



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.