


TORAYFAN CBC3

Applications

- Confections
- Snacks
- Bakery
- Pet Food
- Ag/chem
- Medical



Torayfan CBC3

TRANSPARENT BARRIER COATED, ONE SIDE HEAT SEALABLE BOPP FILM

Summary

One side coated and one side heat sealable Bi-Axially Oriented Polypropylene film with excellent moisture and oxygen barrier. Slip package is added to the sealant for low and consistent COF designed as the outside print web for clear VFFS packages.

Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES	
Thickness		-	0.00001"	70	80
Nominal Yield		-	in ² /lb	44,000	38,300
Tensile Strength at Break	MD	ASTM D882	lb/in ²	21,500	21,500
	TD			45,500	45,500
Young's Modulus	MD	ASTM D882	lb/in ²	350,000	350,000
	TD			600,000	600,000
Elongation at Break	MD	ASTM D882	%	200	200
	TD			60	60
Heat Shrinkage (284°F for 15 minutes)	MD	ASTM D1204	%	8	8
	TD			5	5
Coefficient of Friction (Sealant Side)		ASTM D1894	μ _s	0.34	0.34
			μ _d	0.26	0.26
Haze (1 sheet)		ASTM 1003	%	2.5	2.5
Wetting Tension - Coated Side		ASTM D2578	dyne/cm	60	60
Heat Seal Strength @ 250°F		1	g/in	330	330
Seal Initiation Temp (>200g/in)		1	°F	210	210
MVTR - 100°F, 90% RH		ASTM F1249	g/100in ² /day	0.22	0.20
O ₂ Barrier - 73°F, 0% RH		ASTM D3985	cc/100in ² /day	0.06	0.06

1 Sentinel Sealer model 12 ASL, 0.5 sec, 20 psi. UPPER: flat, Teflon coated. LOWER: rubber with glass cloth, unheated

Important Notes

- The Ultra Barrier Layer should be primed before extrusion lamination
- The Ultra Barrier Layer is not approved for direct contact with food. The surface must be buried in a lamination or through extrusion coating
- The Ultra Barrier Layer is suitable for solvent-based inks. Water-based inks should be avoided.

The product described is covered by one or more of the following patents or patents pending:

US 6844078, EP 1474289, US 9624020 and EP 14874113.5.

Key Features

- Oxygen barrier on par with MOPP
- Alternative to PVdC coated OPP
- 50% improvement in moisture barrier
- Low COF sealant
- Improved oil resistance
- Increased puncture resistance


Similar Products

- CBC2
- CBC

Typical Structures

- CBC3/ink/PE or ADH/F71W
- CBC3/ink/PE or ADH/CBC3 - for superior barrier
- O.L./ink/CBC3

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Torayfan® is a registered trademark of Toray Industries, Inc. for its range of bi-oriented Polypropylene Films (BOPP)