


# TORAYFAN CBP3

# **Applications**

- Confections
- Snacks
- Bakery
- Pet Food
- Ag/chem
- Medical



TRANSPARENT BARRIER COATED, NON-SEALABLE BOPP FILM

# Summary

One side barrier coated, and one side corona-treated with low COF surface Biaxially Oriented Polypropylene film with superior oxygen barrier and excellent moisture barrier. Designed as an outer print film or inner laminating film for transparent barrrier applications.

www.toraytpa.com rimarketing@toraytpa.com Toray Plastics (America), Inc. 50 Belver Avenue North Kingstown, RI 02852 1.800.453.6866



# Torayfan CBP3

## Technical Data \*

| PROPERTIES                                 |    | METHOD       | UNITS     | TYPICAL VALUES |       |
|--|----|--------------|-----------|----------------|-------|
| Thickness                                  |    | -            | micron    | 18             | 20    |
| Nominal Yield                              |    | -            | m²/kg     | 63             | 54    |
| Tensile Strength at Break                  | MD | - ASTM D882  | MPa -     | 100            | 100   |
|  | TD |              |           | 300            | 300   |
| Young's Modulus                            | MD | - ASTM D882  | MPa -     | 2,400          | 2,400 |
|  | TD |              |           | 4,300          | 4,300 |
| Elongation at Break                        | MD | - ASTM D882  | % -       | 200            | 200   |
|  | TD |              |           | 60             | 60    |
| Heat Shrinkage (140°C for 15 min-<br>utes) | MD | - ASTM D1204 | % -       | 8              | 8     |
|  | TD |              |           | 5              | 5     |
| Coefficient of Friction (Treated Side)     |    | ASTM D1894   | μ         | 0.36           | 0.36  |
|  |    |              | $\mu_{d}$ | 0.31           | 0.31  |
| Haze (1 sheet)                             |    | ASTM 1003    | %         | 4              | 4     |
| Wetting Tension - Coated Side              |    | ASTM D2578   | dyne/cm   | 60             | 60    |
| Wetting Tension - Corona Side              |    | ASTM D2578   | dyne/cm   | 41             | 41    |
| MVTR - 38°C, 90% RH                        |    | ASTM F1249   | g/m²/day  | 3.4            | 3.1   |
| O <sub>2</sub> Barrier - 23°C, 0% RH       |    | ASTM D3985   | cc/m²/day | 0.9            | 0.9   |

#### **Important Notes**

• The Ultra Barrier Layer should be primed before extrusion lamination

• The Ultra Barrier Layer is not approved for direct contact with food. The surface must be buried in a lamination or through extrusion coating

• The Ultra Barrier Layer is suitable for solvent-based inks. Water-based inks should be avoided.


### The product described is covered by one or more of the following patents or patents pending: US 6844078, EP 1474289, EP 14874113.5, US 9624020

## Key Features

- · Superior oxygen and excellent moisture barrier
- Alternative to PVdC coated OPP
- 1 side treated with low COF slip non migratory
- Increased stiffness
- Improved oil resistance
- Increased puncture resistance

- Similar Products
- CBS3
- CBP2

- Typical Structures
- F61W/ink/PE or ADH/CBP3/PE/CPP or blown PE
- CBP3/ink/PE or ADH/CBS for superior MVTR
- F61W/PE or ADH/CBP3/cold seal



## \* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Torayfan ® is a registered trademark of Toray Industries, Inc. for its range of bi-oriented Polypropylene Films (BOPP)