


LUMIRROR[®] FR65

Applications

- Hot stamping
- Casting
- Release Liner



Lumirror FR65

PLAIN PET FILM WITH POST INDUSTRIAL RECYCLE

Summary

FR65 is a plain PET film with at least 55% post industrial recycle (PIR) designed for easy handling during processing, especially in hot stamping applications. This film is also designed to avoid the formation of heat wrinkles in the machine direction during drying operations.

Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES							
Thickness		-	micron	11.7	12.2	15.3	19.1	23.4	36.1	50.8	76.3
Nominal Yield		-	m2/kg	61.1	58.5	46.7	37.4	30.5	19.8	14.1	9.4
F-5	MD	ASTM D882	Mpa	104	104	105	106	103	101	102	109
	TD			96	96	94	94	97	94	96	106
Tensile Strength at Break	MD	ASTM D882	Mpa	243	244	238	243	209	171	169	206
	TD			237	236	226	226	237	186	198	213
Young's Modulus	MD	ASTM D882	Mpa	4,854	4,844	4,844	4,854	4,550	4,491	4,452	4,560
	TD			5,296	5,276	4,982	4,913	5,031	5,031	4,962	4,678
Elongation at Break	MD	ASTM D882	%	130	130	130	130	160	170	180	180
	TD			120	120	130	140	130	130	140	160
Heat Shrinkage (150°C for 30 minutes)	MD	ASTM D1204	%	1.6	1.6	1.5	1.5	1.4	1.1	1.2	1
	TD			0.3	0.3	0.1	0.2	0.2	0.2	0.1	1.3
Heat Shrinkage (190°C for 20 minutes)	MD	ASTM D1204	%	3.6	3.5	3.1	3.0	2.7	2.0	2.0	2.0
	TD			0.7	0.7	0.3	0.3	0.8	0.5	0.3	1.8
Coefficient of Friction	A-side vs. B-side	ASTM D1894	μ_s	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.3
			μ_D	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
Haze (1 sheet)		ASTM 1003	%	3.0	3.0	3.5	3.5	3.5	4.0	7.0	5.5


Key Features

- High strength and good handling properties
- Low coefficient of friction which facilitates smooth coating and finishing
- Resistant to heat wrinkle formation in the machine direction during coating process

Similar Products

- F6L
- F7S
- F7R

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Lumirror® is a registered trademark of Toray Industries, Inc. for its range of Polyester Films based on Polyethylene Terephthalate (PET).