


TORAYFAN[®] CBC

Applications

- Confections
- Snacks
- Bakery
- Pet Food
- Ag/Chem
- Medical



Torayfan CBC

ONE SIDE TREATED, ONE
SIDE HEAT SEALABLE
TRANSPARENT BOPP FILM

Summary

One side treated Ultra High Surface Energy (UHSE), one side heat sealable Bi-Axially Oriented Polypropylene film providing excellent moisture barrier. Slip package added to sealant for low and consistent COF. Designed as the outside print web for clear high moisture barrier, VFFS packages.

Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES
Thickness		-	micron	20
Nominal Yield		-	m ² /kg	54
Tensile Strength at Break	MD	ASTM D882	MPa	148
	TD			314
Young's Modulus	MD	ASTM D882	MPa	2,410
	TD			4,140
Elongation at Break	MD	ASTM D882	%	200
	TD			60
Heat Shrinkage (140°C for 15 minutes)	MD	ASTM D1204	%	8
	TD			5
Coefficient of Friction (Sealant Side)		ASTM D1894	μ_s	0.34
			μ_d	0.26
Haze (1 sheet)		ASTM 1003	%	2.5
Wetting Tension		ASTM D2578	dyne/cm	41
Heat Seal Strength @ 121°C		1	g/25mm	330
Seal Initiation Temp (>200g/25mm)		1	°C	99
MVTR - 38°C, 90% RH		ASTM F1249	g/m ² /day	3.1

1 Sentinel Sealer model 12 ASL, 0.5 sec, 20 psi. UPPER: flat, Teflon™ coated. LOWER: rubber with glass cloth, unheated

Key Features

- 50% improvement in moisture barrier
- Alternative to PVdC coated OPP
- Low COF sealant
- Improved oil resistance
- Increased puncture resistance
- Increased stiffness


Similar Products

- CBS

Typical Structures

- CBC/ink/PE or ADH/F71W
- CBC/ink/PE or ADH/CBS - for enhanced MVTR
- O.L./ink/CBC

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Torayfan® is a registered trademark of Toray Industries, Inc. for its range of bi-oriented Polypropylene Films (BOPP)