


TORAYFAN[®] CBP2

Applications

- Confections
- Snacks
- Bakery
- Pet Food
- Ag/Chem
- Medical



Torayfan CBP2

TWO SIDE TREATED, NON SEALABLE TRANSPARENT BOPP FILM

Summary

Two side treated: one side Ultra High Surface Energy (UHSE), one side corona Bi-Axially Oriented Polypropylene. Modified COF on non-UHSE side (non-migratory). Barrier coated for excellent moisture and oxygen barrier. Designed as the outside print or buried web for clear packaging applications requiring excellent moisture barrier.

Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES
Thickness		-	micron	20
Nominal Yield		-	m ² /kg	54
Tensile Strength at Break	MD	ASTM D882	MPa	148
	TD			314
Young's Modulus	MD	ASTM D882	MPa	2,410
	TD			4,140
Elongation at Break	MD	ASTM D882	%	200
	TD			60
Heat Shrinkage (140°C for 15 minutes)	MD	ASTM D1204	%	8
	TD			5
Coefficient of Friction (Lamination Side)		ASTM D1894	μ _s	0.36
			μ _d	0.31
Haze (1 sheet)		ASTM 1003	%	2.5
Wetting Tension - Coated Side		ASTM D2578	dyne/cm	60
Wetting Tension - Corona Side		ASTM D2578	dyne/cm	41
MVTR - 38°C, 90% RH		ASTM F1249	g/m ² /day	3.1
O ₂ Barrier - 23°C, 0% RH		ASTM D3985	cc/m ² /day	3.9

**The product described is covered by one or more of the following patents or patents pending:
EP3086944, US 9624020.**

Important Notes

- Priming of the Ultra Barrier Layer is recommended before extrusion lamination.
- The Ultra Barrier Layer is not approved for direct contact with food. The surface must be buried in a lamination or through extrusion coating
- The Ultra Barrier Layer is suitable for solvent-based inks. Water-based inks should be avoided.

Key Features

- Excellent moisture & oxygen barrier
- Alternative to PVdC coated OPP
- 2 side treated with low COF slip - non migratory
- Improved oil resistance
- Increased puncture resistance
- Increased stiffness


Similar Products

- CBS2
- CBC2

Typical Structures

- CBP2/ink/PE or ADH/F71W
- CBP2/ink/PE or ADH/CBS - for enhanced MVTR
- PET/ink/PE/CBP2/PE
- O.L./ink/CBP2/Patterned Cold Seal
- O.L./ink/Paper/PE/CBP2/PE - metal detection

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Torayfan® is a registered trademark of Toray Industries, Inc. for its range of bi-oriented Polypropylene Films (BOPP)