


TORAYFAN[®] MH5C

Applications

- Confections
- Snacks
- Bakery
- Pet food
- Ag/Chem
- Medical



Torayfan MH5C

ONE SIDE HEAT SEALABLE,
ONE SIDE METALLIZED
BOPP FILM

Summary

One side vacuum deposited Aluminum on Toray's Ultra High Surface Energy (UHSE), one side heat sealable with high seal strength and with improved hermetic seal property. Designed as an inside moisture and oxygen barrier metallized BOPP film for gas flushed applications.

Technical Data *

PROPERTIES		METHOD	UNITS	TYPICAL VALUES	
Thickness		-	micron	17.5	22.5
Nominal Yield		-	m ² /kg	63	48
Tensile Strength at Break	MD	ASTM D882	MPa	148	148
	TD			314	314
Young's Modulus	MD	ASTM D882	MPa	2,180	2,180
	TD			3,780	3,780
Elongation at Break	MD	ASTM D882	%	200	200
	TD			60	60
Heat Shrinkage (140°C for 15 minutes)	MD	ASTM D1204	%	8	8
	TD			5	5
Coefficient of Friction (Sealant Side)		ASTM D1894	μ_s	0.66	0.66
			μ_d	0.45	0.45
Heat Seal Strength @ 121°C		1	g/25mm	1,100	1,400
Seal Initiation Temp (>200g/25mm)		1	°C	88	88
MVTR - 38°C, 90% RH		ASTM F1249	g/m ² /day	0.078	0.078
O2 Barrier - 23°C, 0% RH		ASTM D3985	cc/m ² /day	9.3	9.3

1 Sentinel Sealer model 12 ASL, 0.5 sec, 20 psi. UPPER: flat, Teflon™ coated. LOWER: rubber with glass cloth, unheated

**The product described is covered by one or more of the following patents or patents pending:
US 9120294, and EP 2195161**

Key Features

- Improved sealant design for optimal hermetic sealing
- Superior seal strength
- Good moisture barrier and excellent oxygen barrier
- Non craze metal surface
- Increased oil resistance
- Excellent hot tack and wide heat seal range


Similar Products

- PCFS
- MOTM

Typical Structures

- F62W/ink/ADH or PE/MH5C
- PA10/Ink/PE or ADH/MH5C
- O.L./ink/Paper/PE or ADH/MH5C

Winding Direction



* These values do not constitute specific binding specifications

DISCLAIMER: This information is believed to be correct as of the date of issue. Toray Plastics (America), Inc. MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR COURSE OF PERFORMANCE OR USAGE OF TRADE AND TAKES NO RESPONSIBILITY REGARDING THE SUITABILITY OF THIS INFORMATION FOR THE USER'S INTENDED PURPOSES OR FOR THE CONSEQUENCE OF ITS USE. User is responsible for determining whether the Toray Plastics (America), Inc. product is fit for a particular purpose and suitable for user's method or use of application. Given the variety of factors that can affect the use and application of Toray Plastics (America), Inc. products, which are uniquely within the user's knowledge and control, it is essential that the user make its own tests to determine the safety and suitability of each Toray Plastics (America), Inc. product or product combination for its own purpose.

Torayfan® is a registered trademark of Toray Industries, Inc. for its range of bi-oriented Polypropylene Films (BOPP)